

We help you shine.™

**OMNIGUARD™**  
UHS FLOOR COATING

PROQUIP NZ LTD - 0800 686 284 - [www.proquipnz.co.nz](http://www.proquipnz.co.nz)

# 141 OMNIGUARD™

shine on.

## UHS FLOOR COATING

For high traffic areas that require a durable and easy to maintain surface, **OMNIGUARD** is the obvious choice. The high solid formulation of this UHS floor finish produces extreme gloss that withstands the effects of crowded market places in any weather condition.

### Product Packaging\*



PROD CODE: 141FSE  
 SIZE: 10 litres  
 ORDER QTY: 2 per case

A **high-solids** “wet-look” shine that’s **easy** to maintain.

### Recommended Floor Surfaces:

Vinyl composition tile (“VCT”), terrazzo, marble, concrete, quarry tile.

#### Directions for use: INITIAL APPLICATION

For a floor that has been stripped, properly neutralized, rinsed and allowed to dry thoroughly, apply 4-5 thin coats of **OMNIGUARD** Floor Coating using a clean synthetic mop.

Allow the floor to dry thoroughly between coats and prior to burnishing.

Optional: Apply 2 thin coats of Pioneer Eclipse floor sealer for old or porous floors or for high traffic areas plus 2-3 coats of **OMNIGUARD** Floor Coating.

For a floor that has been deep scrubbed and allowed to dry thoroughly, apply 1-2 thin coats of **OMNIGUARD** Floor Coating using a clean synthetic mop. Allow floor to dry thoroughly between coats and prior to burnishing.

#### Directions for use: ROUTINE MAINTENANCE


1. Sweep floor daily with a dust mop.
2. To clean floor use a mop or automatic scrubber with neutral cleaner.
3. Restore shine as needed with our floor maintainer.
4. Burnish as desired with ultra high speed machine and pad.
5. As needed, perform a deep scrub and re-coat applying an additional 1-2 coats of **OMNIGUARD** Floor Coating.
6. Allow floor to dry thoroughly between coats and prior to burnishing.
7. Strip floor when desired results cannot be achieved with routine maintenance.

### Product Data:

<b>Description</b>	Polymer emulsion	<b>Coverage</b>	2500 to 3000 ft <sup>2</sup> /gal 61 to 74 m <sup>2</sup> /liter	<b>Buffability</b>	Excellent
<b>Appearance</b>	Milky white	<b>Fragrance</b>	Mild odor No fragrance added	<b>Removability</b> ASTM D1792-06	Excellent
<b>Non-volatile solids</b> ASTM D2834-95 (2008)	25%	<b>Slip Resistance</b> UL TM410	Meets requirements	<b>Detergent Resistance</b> ASTM D3207-92 (2008)	Excellent
<b>Specular Gloss (60°)</b> ASTM D1455-87 (2008)	>85	<b>Shelf Life</b> ASTM D1791-93 (2008)	1 year	<b>Drying Time</b>	About 25 minutes
<b>Viscosity (Brookfield)</b> @ 68°F (20°C)	<10 centipoise	<b>Density</b> ASTM D1475-98 (2008)	8.5 lb/gal @ 68°F 1.03 kg/L @ 20°C	<b>Freeze/Thaw</b> ASTM D3209-93 (2008)	Passes 3 cycles

MSDS sheets available for download at [www.pioneer-eclipse.com](http://www.pioneer-eclipse.com)

**VOC** 0.06%  
(40 CFR Part 59 Subpart C)

 Floor Coating and Finishing materials  
as to slip resistance only. 42E6 141\_PDS 1/13

Distributed in New Zealand by



© 2013 Amano Pioneer Eclipse Corporation® • 1 Eclipse Road • PO Box 909 • Sparta, NC 28675 USA  
 1-800-367-3550 • 1-336-372-8080 • Fax: 1-336-372-2895 • [www.pioneer-eclipse.com](http://www.pioneer-eclipse.com)